

AP20 Rec'd PCT/PTO 05 JUN 2006

## Description

# SUPER RESOLUTION INFORMATION STORAGE MEDIUM AND METHOD OF PREVENTING THE SAME FROM DETERIORATION

### Technical Field

- [1] The present invention relates to a super resolution information storage medium and a method of preventing the same from deterioration, and more particularly, to an information storage medium of reproducing information, which is recorded as marks smaller than the resolution of a reproducing beam, and of preventing deterioration due to repeated reproduction and a method of preventing the same from deterioration.

### Background Art

- [2] An optical recording medium is used as an information storage medium for an optical pickup device of recording and reproducing information in a non-contact type. As industries are developed, it is required to increase the recording density of information. To this end, an information storage medium of reproducing information having recording marks of smaller than the resolution of a laser beam, by using a super resolution phenomenon, is developed.
- [3] Examples of an information storage medium include a read only memory (ROM) for reproducing recorded information, a write once read many memory for possibly recording once, and a rewritable memory for possibly erasing and rewriting information.
- [4] Here, in the case of the ROM, information is recorded on a substrate in a pit type, and the information is reproduced by using the reflectivity difference of reproducing beams. In other words, the information is reproduced by using the fact that the reflectivity amount of the beam is large where pits exist and the reflectivity amount of the beam is small where pits are absent.
- [5] As technologies are developed, performances required to the information storage medium are increased, most of all, the capacity of the storage medium. The increase of the capacity of the storage medium depends on how small can marks be recorded in a limited area of the storage medium and how precisely can the recorded marks be reproduced.
- [6] More specifically, the performance of reproducing information depends on the decrease of the wavelength of a light source, which is used to reproduce the information, and the increase of the numerical aperture of an object lens. However, there

is a limit in providing a laser having a short wavelength, and the cost of manufacturing an object lens with a large numerical aperture is high. In addition, as the numerical aperture of the object lens is increased, a working distance between an optical pickup and an information storage medium is reduced, thus the optical pickup may collide against the information storage medium and the information recorded on the storage medium may be damaged. Accordingly, it is difficult to increase the capacity and the density of an information storage medium.

- [7] Furthermore, when the wavelength of a light source for reproducing information from a storage medium is  $\lambda$  and the numerical aperture of an object lens is NA,  $\lambda/4NA$  is the limit of a reproducing resolution, thus the reproduction of information from the storage medium may be impossible even when recording marks are formed to be extremely small. In other words, a beam radiated from a light source cannot distinguish the recording marks smaller than  $\lambda/4NA$ , thus the reproduction of the information is impossible.

## **Disclosure of Invention**

### **Technical Problem**

- [8] However, a super resolution phenomenon, which reproduces the recorded marks having a size exceeding the limit of a resolution, occurs, and studies of the super resolution phenomenon are performed. According to the super resolution phenomenon, the recorded marks having a size of exceeding the limit of the resolution can be reproduced, thus a super resolution storage medium can increase the density and the capacity of the medium.
- [9] In order to widely use a super resolution storage medium, recording characteristics and reproducing characteristics required as an information storage medium should be satisfied. Here, the most important characteristic is a tracking error signal. More specifically, the super resolution information storage medium uses a recording beam and a reproducing beam whose powers are relatively higher than those used for a conventional information storage medium, thus it is important to normally detect the tracking error signals.

### **Technical Solution**

- [10] The present invention provides an information storage medium for securing reproducing stability and reliability by preventing a reproducing characteristic from being deteriorated caused by repeatedly radiating a reproducing beam, and a method of preventing the same from deterioration.
- [11] According to an aspect of the present invention, there is provided an information

storage medium of reproducing information, which is recorded as marks smaller than a resolution of an incidence beam, comprising a substrate and a super resolution layer directly arranged on the substrate without any layer therebetween to reproduce the marks by generating a thermal reaction at a portion where the incidence beam is focused.

- [12] The marks may be formed on the substrate in a pit type.
- [13] The super resolution layer may be formed of any one material selected from metal oxides formed of  $\text{PtO}_x$ ,  $\text{AuO}_x$ ,  $\text{PdO}_x$ , and  $\text{AgO}_x$ , or a polymer compound.
- [14] The information storage medium may further include at least one thermal absorption layer of absorbing the heat of the incidence beam.
- [15] The thermal absorption layer may be formed of any one of a Ge-Sb-Te-based alloy and an Ag-In-Sb-Te-based alloy.
- [16] A dielectric layer may be arranged between the super resolution layer and each of at least one thermal absorption layer.
- [17] According to another aspect of the present invention, there is provided an information storage medium of reproducing information, which is recorded as marks smaller than a resolution of an incidence beam, comprising a substrate and a thermal absorption layer directly arranged on the substrate without any layer therebetween to reproduce the marks by generating a thermal absorption at a portion where a reproducing beam is focused.
- [18] According to still another aspect of the present invention, there is provided a method of preventing a reproducing characteristic from being deteriorated when reproducing information, which is recorded as marks, from an information storage medium including a substrate on which the marks smaller than a resolution are recorded and a thermal absorption layer and/or a super resolution layer possibly reproducing the marks, the method comprising radiating a reproducing beam higher than a predetermined temperature to the substrate to generate a thermal reaction on the thermal absorption layer and/or the super resolution layer, and exhausting a heat from the reproducing beam from the substrate by omitting a layer of disturbing the flow of the heat from the reproducing beam between the substrate and the thermal absorption layer or the substrate and the super resolution layer.

#### **Advantageous Effects**

- [19] As described above, an information storage medium according to the present invention can reproduce super resolution information by preventing the deterioration of the reproducing characteristic due to the repeated reproduction of the information

storage medium, when reproducing information recorded as marks smaller than a resolution. Thus, the recording density and capacity of the information storage medium can be increased.

[20] According to the present invention, a layer of preventing the flow of heat, which is from a reproducing beam, is not formed on a substrate. Accordingly, when the reproducing beam is radiated to reproduce data from the information storage medium, the heat from the reproducing beam is sufficiently exhausted to the outside and the deterioration of the information storage medium by repeatedly reproducing the information storage medium can be prevented.

[21] The information storage medium according to the present invention is formed by arranging five layers or seven layers on a substrate and the material of a super resolution layer is limited; however, the number of layers and the material of the super resolution layer can vary.

### **Description of Drawings**

[22] The above and other features and advantages of the present invention will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings in which:

[23] FIGS. 1A and 1B are sectional views illustrating information storage media according to a first embodiment of the present invention;

[24] FIG. 2 is a sectional view illustrating an information storage medium according to a second embodiment of the present invention;

[25] FIG. 3A is a sectional view illustrating an information storage medium, which is formed to measure a tracking error signal, according to the present invention;

[26] FIG. 3B is a sectional view illustrating a conventional information storage medium having a dielectric material that is formed to measure and compare a tracking error signal with that of an information storage medium according to the present invention;

[27] FIGS. 4A through 4E illustrate the results of tracking error signals measured by changing the power of a reproducing beam on an information storage medium according to the present invention;

[28] FIGS. 5A through 5E illustrate the results of tracking error signals measured by changing the power of a reproducing beam on a conventional information storage medium; and

[29] FIG. 6 is a block diagram illustrating a recording/reproducing system of an information storage medium according to the present invention.

### **Mode for Invention**

- [30] The present invention will now be described more fully with reference to the accompanying drawings, in which exemplary embodiments of the invention are shown.
- [31] An information storage medium according to the present invention is a super resolution information storage medium for reproducing information, which is recorded as marks having a size exceeding a resolution limit.
- [32] Referring to FIG. 1A, an information storage medium according to a first embodiment of the present invention includes a substrate 10, at least one super resolution layer 18, and at least one thermal absorption layer 14. Here, the super resolution layer 18 thermally reacts with a reproducing beam to occur a super resolution phenomenon, and the thermal absorption layer 14 absorbs the heat from the radiation of the reproducing beam in order to induce the super resolution phenomenon with the super resolution layer 18.
- [33] The thermal absorption layer 14 or the super resolution layer 18 is directly formed on the substrate 10. In other words, the thermal absorption layer 14 or the super resolution layer 18 is formed on the substrate 10 without an insertion layer therebetween.
- [34] In the information storage medium shown in FIG. 1A, the thermal absorption layer 14 is directly formed on the substrate 10, and the super resolution layer 18 is formed on the thermal absorption layer 14. Here, a first dielectric layer 16 may be formed between the thermal absorption layer 14 and the super resolution layer 18, and a second dielectric layer 20 may be formed on the super resolution layer 18.
- [35] The substrate 10 is formed of any one material selected from polycarbonate, polymethylmethacrylate (PMMA), amorphous polyolefin (APO), and glass. Pits p as recording marks are formed on the substrate 10 to record information. Here, length of the pits p is smaller than a resolution.
- [36] The super resolution layer 18 may be formed of a metal oxide or a polymer compound. For example, the super resolution layer 18 may be formed of at least one metal oxide selected from  $\text{PtO}_x$ ,  $\text{PdO}_x$ ,  $\text{AuO}_x$ , and  $\text{AgO}_x$ . In addition, the examples of the polymer compound are  $\text{C}_{32}^x\text{H}_{18}^x\text{N}_8^x$  and  $\text{H}_2^x\text{PC}$  (phthalocyanine). The super resolution layer 18 induces the super resolution phenomenon by thermally reacting with the reproducing beam.
- [37] The thermal absorption layer 14 helps the super resolution layer 18 to reproduce the marks smaller than the resolution when the super resolution layer 18 thermally reacts with the reproducing beam.
- [38] The thermal absorption layer 14 may be formed of a Ge-Sb-Te-based alloy or an

Ag-In-Sb-Te-based alloy. The optical characteristic of the thermal absorption layer 14 is changed by the reproducing beam to assist the transformation of the super resolution layer 18. On the other hand, the reproducing beam may be radiated from a lower portion of the substrate 10 toward the substrate 10 or from the opposite direction of the substrate 10.

- [39] The thermal absorption layer 14 may be arranged below or above the super resolution layer 18, and it is preferable that the thermal absorption layer 14 is arranged near the direction of radiating the reproducing beam. In other words, when the reproducing beam is radiated from the opposite direction of the substrate 10, the thermal absorption layer 14 is arranged above the super resolution layer 18. When the reproducing beam is radiated from the lower portion of the substrate 10, the thermal absorption layer 14 is arranged below the super resolution layer 18. When the reproducing beam is radiated from the opposite direction of the substrate 10, a cover layer (not shown) may be further arranged.
- [40] FIG. 1B is a sectional view illustrating an information storage medium in which a thermal absorption layer 14 is arranged above a super resolution layer 18. Here, the super resolution layer 18 is formed on a substrate 10 without any layer therebetween.
- [41] In addition, a first dielectric layer 16 is formed between the super resolution layer 18 and the thermal absorption layer 14, and a second dielectric layer 20 is formed on the thermal absorption layer 14.
- [42] An information storage medium according to a second embodiment of the present invention will now be described with reference to FIG. 2.
- [43] Referring to FIG. 2, an information storage medium according to the second embodiment of the present invention includes a substrate 30 and a first thermal absorption layer 32, which is directly formed on the substrate 30 without any layer therebetween. The information storage medium according to the second embodiment of the present invention includes two thermal absorption layers that is different from the information storage medium according to the first embodiment of the present invention.
- [44] The first thermal absorption layer 32 is directly formed on the substrate 30, and a super resolution layer 36 is formed above the first thermal absorption layer 32. A second thermal absorption layer 40 is formed above the super resolution layer 36.
- [45] In addition, a first dielectric layer 34 is formed between the first thermal absorption layer 32 and the super resolution layer 36, a second dielectric layer 38 is formed between the super resolution layer 36 and the second thermal absorption layer 40, and

a third dielectric layer 42 is formed on the second thermal absorption layer 40.

[46] Here, the locations of the first thermal absorption layer 32 and the super resolution layer 36 can be exchanged.

[47] When an information storage medium has two thermal absorption layers, the information storage medium generates a better reproducing signal characteristic than an information storage medium having one thermal absorption layer.

[48] The substrate 30, the super resolution layer 36, and the thermal absorption layers 32 and 40 are the same as those of an information storage medium according to the first embodiment of the present invention, thus the descriptions thereof will be omitted.

[49] Hereafter, the process of reproducing data from an information storage medium according to the present invention will be described. A reproducing beam is radiated to an information storage medium to reproduce data, then plasmons having a shorter wavelength than the reproducing beam are generated from metal particles of super resolution layers 18 and 36 to which the reproducing beam is radiated and the plasmons are excited to reproduce marks smaller than a resolution. Here, the optical characteristics of thermal absorption layers 14, 32, and 40 may be changed due to the reproducing beam to affect the super resolution layers 18 and 36.

[50] In order to induce thermal reactions in the super resolution layers 18 and 36 and the thermal absorption layers 14, 32, and 40 to reproduce the marks smaller than the resolution, a reproducing beam with a higher power than a beam used to reproduce a conventional information storage medium is used. Here, the conventional information storage medium denotes an information storage medium from which data is reproduced by a conventional method, other than a super resolution phenomenon.

[51] Since the power of the reproducing beam used for the super resolution information storage medium is high, it is expected that a reproducing characteristic of the super resolution information storage medium will be deteriorated by repeatedly radiating the reproducing beam. When the reproducing characteristic of the information storage medium is deteriorated, the data cannot be reproduced. Accordingly, it is required to prevent the reproducing characteristic of the super resolution information storage medium from being deteriorated.

[52] In the information storage medium according to the present invention, the thermal absorption layer 14 or 32 or the super resolution layer 18 or 36 is directly formed on the substrate 10 or 30 to prevent the reproducing characteristic from being deteriorated.

[53] In order to measure the improvement of the reproducing characteristic of the in-

formation storage medium according to the present invention, tracking error signals of an information storage medium in which an insertion layer is not formed between a substrate 10 or 30 and a thermal absorption layer 14 or 32 or a substrate 10 or 30 and a super resolution layer 18 or 36, and an information storage medium in which a dielectric layer is inserted between a substrate 10 or 30 and a thermal absorption layer 14 or 32 or a substrate 10 or 30 and a super resolution layer 18 or 36 are detected.

[54] An information storage medium according to the present invention is formed of a substrate formed to a thickness of 1.1 mm, a thermal absorption layer of Ge-Sb-Te formed to a thickness of 33 nm, a first dielectric layer of  $\text{ZnS-SiO}_2$  formed to a thickness of 25 nm, a super resolution layer of  $\text{PtO}_x$  formed to a thickness of 3.5 nm, and a second dielectric layer of  $\text{ZnS-SiO}_2$  formed to a thickness of 30 nm, as shown in FIG. 3A in order to measure tracking error signals.

[55] An information storage medium as a comparative example is formed of a substrate formed to a thickness of 1.1 mm, a first dielectric layer of  $\text{ZnS-SiO}_2$  formed to a thickness of 20 nm, a thermal absorption layer of Ge-Sb-Te formed to a thickness of 33 nm, a second dielectric layer of  $\text{ZnS-SiO}_2$  formed to a thickness of 25 nm, a super resolution layer of  $\text{PtO}_x$  formed to a thickness of 3.5 nm, and a third dielectric layer of  $\text{ZnS-SiO}_2$  formed to a thickness of 30 nm, as shown in FIG. 3B.

[56] FIGS. 4A through 4E illustrate tracking error signals of the information storage medium according to the present invention that are measured while varying the power of a reproducing beam. The tracking error signals of FIG. 4A are obtained by reproducing the information storage medium for one minute by using a reproducing power of 1.0 mW. In addition, the tracking error signals of FIGS. 4B through 4E are obtained by reproducing the information storage medium for one minute by using reproducing powers of 1.2 mW, 1.4 mW, 1.6 mW, and 1.8 mW, respectively. The tracking error signals are excellent when the reproducing power is in a range from 1.0 to 1.6 mW. When the reproducing power is 1.8 mW, the tracking error signals are bad.

[57] FIGS. 5A through 5E illustrate tracking error signals of the information storage medium as the comparative example that are measured while varying the power of a reproducing beam. The tracking error signals of FIGS. 5A through 5E are obtained by reproducing the information storage medium as the comparative example for one minute by using reproducing powers of 1.0, 1.1, 1.2, 1.3, and 1.4 mW. In the case of the information storage medium as the comparative example, the tracking error signals are bad even when the reproducing power is 1.0 mW. When the reproducing power is larger than 1.0 mW, the tracking error signals are rapidly deteriorated. According to

the result of the tracking error signals, the tracking error signals are unstable when reproducing the information storage medium as the comparative example, thus the tracking operation cannot be performed due to the fluctuation of the tracking error signals and the deterioration becomes serious.

[58] When considering the result of the tracking error signals, the reproducing characteristic of an information storage medium can be improved by directly arranging a thermal absorption layer or a super resolution layer on a substrate. Accordingly, it is known that when reproducing data from the information storage medium by using a high reproducing power, deterioration degree and speed can be reduced by using the information storage medium according to the present invention.

[59] In addition, a heat generated from the radiation of a laser beam for reproducing data is accumulated on an information storage medium, thus the tracking error signals are deteriorated in the case of the information storage medium as the comparative example. Accordingly, the deterioration due to the heat can be efficiently prevented by not arranging a layer, which prevents the exhaustion of heat, between a substrate and a thermal absorption layer or a substrate and a super resolution layer.

[60] Hereafter, a method of preventing the reproducing characteristic of an information storage medium according to the present invention from being deteriorated will be described. First, data is recorded in a pit type smaller than a resolution, on a substrate 10 or 30 of FIGS. 1A, 1B, and 2. Then, a reproducing beam of higher than a predetermined temperature is radiated to occur a thermal reaction on a thermal absorption layer 14, 32, or 40 and a super resolution layer 18 or 36. Here, the thermal absorption layer 14 or 32 or the super resolution layer 18 or 36 is directly formed on the substrate 10 or 30, without any layer therebetween, in order to efficiently exhaust the heat from the reproducing beam.

[61] In other words, a layer of preventing the flow of the heat from the reproducing beam is not formed between the substrate 10 or 30 and the thermal absorption layer 14 or 32 or the substrate 10 or 30 and the super resolution layer 18 and 36, thus the heat from the reproducing beam is efficiently exhausted to the outside when radiating the reproducing beam to reproduce data from the information storage medium. Accordingly, the deterioration of the information storage medium by repeatedly reproducing the information storage medium can be prevented.

[62] FIG. 6 is a block diagram illustrating a system of recording/reproducing an information storage medium according to the present invention. A system of recording/reproducing an information storage medium includes a pickup unit 50, a recording/

reproducing signal process unit 60, and a control unit 70. More specifically, the system includes a laser diode 51 of radiating a beam, a collimating lens 52 of collimating the beam radiated from the laser diode 51, a beam splitter 54 of converting the path of an incidence beam, and an object lens 56 of concentrating the beam from the beam splitter 54 on an information storage medium D.

[63] The beam reflected on the information storage medium D is reflected by the beam splitter 54 and received by an optical detector, for example, a quad-optical detector 57. The beam received by the optical detector 57 is converted into electric signals by an operation circuit unit 58 and output as a channel 1 Ch1 signal, which is detected as an RF signal, in other words, a sum signal, and a differential signal channel Ch2, which detects a push-pull type signal.

[64] The control unit 70 radiates a reproducing beam of over a predetermined power, which is required according to the material characteristic of an information storage medium, through the pickup unit 50, in order to reproduce marks smaller than a resolution. When the reproducing beam is focused on the information storage medium D through the pickup unit 50, a super resolution phenomenon occurs on the information storage medium D. The super resolution phenomenon of the information storage medium D according to the present invention is described above, thus the descriptions thereof will be omitted.

[65] The beam reflected from the information storage medium D is input to the optical detector 57 through the object lens 56 and the beam splitter 54. The signals input to the optical detector 57 are converted into electric signals by the operation circuit unit 58 and output as RF signals. C/N stability of the information storage medium D is improved due to a thermal conductive layer 20 or 40 of FIGS. 1A, 1B, and 2, thus the reproducing characteristic is not deteriorated even after the information storage medium D is repeatedly reproduced. Accordingly, the signal process unit 60 and the control unit 70 can sufficiently record/reproduce data.

[66] While the present invention has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims.